



Phone: 724-715-7266 • Fax: 724-715-7341 • www.kimestech.com

JALPON[™] 1300A Gelled Calcium Sulfonate Blend in Aliphatic Solvent

GENERAL DESCRIPTION

Jalpon[™] 1300A is a thixotropic gelled overbased calcium sulfonate in mineral spirits containing waxes and other proprietary ingredients. A variety of solvent based industrial coatings can be made by incorporating materials such as resins, waxes, asphalts, oils and/or other ingredients. Specialty coatings can be developed which impart superior corrosion protection, flow control, high film build, and sag resistance.

TYPICAL PROPERTIES (NOT SPECIFICATIONS)

		J1300A
Non-volatile, Wt. %	ASTM D2369	60
Viscosity, Brookfield #6 @ 10 rpm, cP	ASTM D2196	40,000 - 65,000
Flash Point, °F (°C)	ASTM D93	104 (40)
Density, Pounds per Gallon @ 15.6°C	ASTM D1475	8.0

APPLICATIONS

Jalpon[™] 1300A is an excellent formulating base. It can also be used "as is" for a soft, waxy automotive undercoating to prevent rust and corrosion. For heavier duty undercoats and truck and trailer frame coatings, Jalpon[™] 1300A can be blended with waxes, oils, asphalts, and/or pigments. Jalpon[™] 1300A is REACh registered.

AVAILABILITY

Jalpon[™] 1300A is available in 55-Gallon Open Head Drums.

10-28-2019